

<b>Bricklayers White<sup>®</sup> Cement</b>		
<b>Standard</b>		<b>Type</b>
AS 1316-2003		Masonry Composite Cement
<b>Physical Properties</b>		<b>Typical Results</b>
Hunter L		93.6
Air Content	%	15
Water Retention	%	75
Fineness (Blaine)	m <sup>2</sup> /kg	400
Density	g/cm <sup>3</sup>	3.1
Initial Setting Time	minutes	140
Final Setting Time	minutes	170
<b>Compressive Strength</b>		<b>AS 1316-2003</b>
7 days	MPa	22
28 days	MPa	31