

WHITE PORTLAND CEMENT

AALBORG WHITE® KNIGHT BRAND	
Type	CEM I 52.5N
Strength class	52.5N
Fe ₂ O ₃	0.2%
SO ₃	3.3%
Chloride	0.01%
L.O.I	3.0%
Insoluble residue	0.2%
Equivalent alkalies (Na ₂ O)	0.4%
Fineness (Blaine)	3980cm ² /g
Le Chatelier expansion	2mm
2 day strength	32.0MPa
28 day strength	64.0MPa
Initial setting time (Vicat)	155min
Whiteness (Hunter)	91.5